100% dielectric gratings offer unbeatable environmental and thermal stability combined with high efficiency, low PDL performance



Polarization independent (PING) telecom gratings from Ibsen are produced by holographic/lithographic stepper technology in 100% dielectric materials. This leads to unbeatable thermal and environmental stability, with no polymers, epoxies, gelatins or metals in the optical path nor in the grating whatsoever.



PING Grating


940 I/mm PING for telecom C-band

PING-Sample-003

940 I/mm PING Grating for telecom C-band

PING-Sample-003

Benefits High efficiency, low PDL, broad spectral bandwidth Transmission gratings give much greater alignment tolerances Low transmitted wavefront distortion High tolerance to illumination angle of incidence Two grating designs are possible, offering compact design possibilities Unbeatable thermal & environmental stability & lifetime




Parameter	Specification
Materials	100% dielectric materials
Grating area	19 mm x 13.5 mm
Chip size	21 mm x 15 mm
Chip thickness	0.625 mm
Grating resolution	940 l/mm
PDL	<0.25 dB
Angle of incidence (AOI)	46.6 degrees
Diffraction efficiency (TE & TM)	>90%
Bandwidth	1526 nm – 1566 nm
Production technology	Holographic/lithographic stepper and RIE etching
Maximum operating temperature	>500 degrees C
Pagkaging and shipment	Gelpak containers. Manufactured and sealed in class 10 cleanroom
Cleaning recommendation	First contact. Available from Photonic Cleaning




940 I/mm PING Grating for telecom C-band

PING-Sample-003

Typical grating performance



Diffraction efficiency vs incident angle







940 I/mm PING Grating for telecom C-band

PING-Sample-003

Configuration/Definitions



Drawing



Specifications are subject to change without notice.

The above grating is an example of Ibsen's capabilities. Ibsen operates as grating partner for our customers, from being an integrated part of the grating and device / instrument design phase, to the manufacturing of prototypes, to volume manufacturing of OEM gratings.

