100% dielectric gratings offer unbeatable environmental and thermal stability combined with high efficiency, low PDL performance



Polarization independent (PING) telecom gratings from Ibsen are produced by holographic/lithographic stepper technology in 100% dielectric materials. This leads to unbeatable thermal and environmental stability, with no polymers, epoxies, gelatins or metals in the optical path nor in the grating whatsoever.

Advanced etching technology ensures highest diffraction efficiency and lowest PDL over a very broad bandwidth. Low angular sensitivity is an added bonus for module design and assembly.

PING Grating

1144 I/mm PING for telecom O-band PING-Sample-106

1144 I/mm PING Grating for telecom O-band

PING-Sample-106

Benefits

 High efficiency, low PDL, broad spectral bandwidth


 Transmission gratings give much greater alignment tolerances

 Low transmitted wavefront distortion

 High tolerance to illumination angle of incidence

 Two grating designs are possible, offering compact design possibilities

 Unbeatable thermal & environmental stability & lifetime



Parameter	Specification
Materials	100% dielectric materials
Grating area	14 mm x 11.5 mm
Chip size	16 mm x 13.5 mm
Chip thickness	0.625 mm
Grating resolution	1143.9 l/mm
PDL	<0.25 dB
Angle of incidence (AOI)	49.9 degrees
Diffraction efficiency (TE & TM)	>90%
Bandwidth	1274 nm – 1346 nm
Production technology	Holographic/lithographic stepper and RIE etching
Maximum operating temperature	>500 degrees C
Pagkaging and shipment	Gelpak containers. Manufactured and sealed in class 10 cleanroom
Cleaning recommendation	First contact. Available from Photonic Cleaning




For further information you can contact us directly at:

Ibsen Photonics A/S Phone +45 4434 7000 Ryttermarken 15-21 Fax +45 4434 7001 DK-3520 Farum www.ibsen.com

Denmark E-mail inquiry@ibsen.com


1144 I/mm PING Grating for telecom O-band **PING-Sample-106**

Typical grating performance





Diffraction efficiency vs incident angle



V bsen photonics

For further information you can contact us directly at:


Ibsen Photonics A/S Phone +45 4434 7000 Ryttermarken 15-21 Fax +45 4434 7001

DK-3520 Farum www.ibsen.com


Denmark E-mail inquiry@ibsen.com

1144 I/mm PING Grating for telecom O-band PING-Sample-106

Configuration/Definitions



Drawing



Specifications are subject to change without notice.

The above grating is an example of Ibsen's capabilities. Ibsen operates as grating partner for our customers, from being an integrated part of the grating and device / instrument design phase, to the manufacturing of prototypes, to volume manufacturing of OEM gratings.

Ibsen photonics For further information you can contact us directly at:

Ibsen Photonics A/S Phone +45 4434 7000 Ryttermarken 15-21 Fax +45 4434 7001 DK-3520 Farum www.ibsen.com Denmark E-mail inquiry@ibsen.com